

SIGMASHIELD 420 LT**(SIGMA MULTIGUARD LT)**

4 pages

January 2007
Revision of September 2005

DESCRIPTION	two component reinforced high solids polyamine adduct cured epoxy coating
PRINCIPAL CHARACTERISTICS	<ul style="list-style-type: none"> – coating for cargo tanks of bulk- or oil carriers and storage tanks – buildcoat for underwater- and boottop systems – good low temperature curing – excellent abrasion and impact resistance – excellent water resistance – easy to clean
COLOURS AND GLOSS	grey, redbrown (other colours on request) - gloss
BASIC DATA AT 10°C	(1 g/cm ³ = 8.25 lb/US gal; 1 m ² /l = 40.7 ft ² /US gal) (data for mixed product)
Mass density	1.6 g/cm ³
Volume solids	84 ± 2%
VOC (supplied)	max. 123 g/kg (Directive 1999/13/EC, SED) max. 191 g/l (approx. 1.6 lb/gal)
Recommended dry film thickness	150 - 200 µm depending on system
Theoretical spreading rate	5.6 m ² /l for 150 µm, 4.2 m ² /l for 200 µm *
Overcoating interval	min. 10 hours * max. 14 days *
Full cure after	7 days * (data for components)
Shelf life (cool and dry place)	at least 12 months * see additional data
RECOMMENDED SUBSTRATE CONDITIONS AND TEMPERATURES	<ul style="list-style-type: none"> – previous coat; (e.g. SigmaCover 280 LT or SigmaShield 220 LT) dry and free from ice and any contamination – substrate temperature should be between -10°C up to 15°C during application and curing and at least 3°C above dew point and free from ice and any contamination – during application and curing a substrate temperature down to -10°C is possible, but curing to hardness takes longer and complete resistance will be reached when temperature increases – maximum relative humidity during application and curing is 85%
SYSTEM SPECIFICATION	marine system sheets 3101, 3102, 3103, 3107

SIGMASHIELD 420 LT

(SIGMA MULTIGUARD LT)

January 2007

INSTRUCTIONS FOR USE

mixing ratio by volume: base to hardener 75 : 25

- the temperature of the mixed base and hardener should preferably be above 5°C, otherwise extra solvent may be required to obtain application viscosity
- too much solvent results in reduced sag resistance and slower cure
- thinner should be added after mixing the components

Induction time

none

Pot life

1 hour at 10°C *
* see additional data

AIRLESS SPRAY

Recommended thinner
Volume of thinner

Sigma thinner 91-92
0 - 5% for 200 µm dft,
10% for 100 µm dft

Nozzle orifice
Nozzle pressure

approx. 0.53 - 0.68 mm (= 0.021 - 0.027 in)
15 MPa (= approx. 150 bar; 2130 p.s.i.)

AIR SPRAY

Recommended thinner
Volume of thinner
Nozzle orifice
Nozzle pressure

Sigma thinner 91-92
5 - 10%, depending on required thickness and application conditions
1.7 - 2 mm
0.3 - 0.4 MPa (= approx. 3 - 4 bar; 43 - 57 p.s.i.)

BRUSH/ROLLER

Recommended thinner
Volume of thinner

Sigma thinner 91-92
0 - 5%

CLEANING SOLVENT

Sigma thinner 90-53

SAFETY PRECAUTIONS

for paint and recommended thinners see safety sheets 1430, 1431 and relevant material safety data sheets

this is a solvent based paint and care should be taken to avoid inhalation of spray mist or vapour as well as contact between the wet paint and exposed skin or eyes

ADDITIONAL DATA

Film thickness and spreading rate

theoretical spreading rate m ² /l	8.4	5.6	4.8	4.2
dft in µm	100	150	175	200

max. dft when brushing:

75 µm

SIGMASHIELD 420 LT

(SIGMA MULTIGUARD LT)

January 2007

Overcoating table for various epoxy products for dft up to 200 µm

substrate temperature	-10°C	0°C	5°C	10°C	15°C
minimum interval	48 hours	24 hours	10 hours	5 hours	4 hours
maximum interval	28 days	28 days	28 days	14 days	10 days

- surface should be dry and free from chalking and contamination

Curing table for dft up to 200 µm

substrate temperature	dry to handle	full cure for immersion in seawater	full cure
-10°C	34 hours	18 days	--
0°C	17 hours	10 days	28 days
5°C	12 hours	7 days	14 days
10°C	6 hours	5 days	7 days
15°C	4 hours	4 days	5 days

- for cargo hold application: for full cure for hard angular cargoes, please contact your nearest SigmaKalon Marine & Protective Coatings sales office
- adequate ventilation to remove solvent must be maintained during application and curing (please refer to sheet 1433 and 1434)
- should SigmaShield 420 LT or the total coating system (2 x 125 µm) be applied in excess of the specified dry film thickness, than the time necessary to reach full cure will be increased

Pot life (at application viscosity)

5°C	2 hours
10°C	1 hour

Worldwide availability

Whilst it is always the aim of SigmaKalon Marine & Protective Coatings to supply the same product on a worldwide basis, slight modification of the product is sometimes necessary to comply with local or national rules/circumstances.

Under these circumstances an alternative product data sheet is used.

SIGMASHIELD 420 LT

(SIGMA MULTIGUARD LT)

January 2007

REFERENCES

Explanation to product data sheets	see information sheet 1411
Safety indications	see information sheet 1430
Safety in confined spaces and health safety	
Explosion hazard - toxic hazard	see information sheet 1431
Safe working in confined spaces	see information sheet 1433
Directives for ventilation practice	see information sheet 1434

LIMITATION OF LIABILITY

The information in this data sheet is based upon laboratory tests we believe to be accurate and is intended for guidance only. All recommendations or suggestions relating to the use of the Sigma Coatings products made by SigmaKalon Marine & Protective Coatings, whether in technical documentation, or in response to a specific enquiry, or otherwise, are based on data which to the best of our knowledge are reliable. The products and information are designed for users having the requisite knowledge and industrial skills and it is the end-user's responsibility to determine the suitability of the product for its intended use.

SigmaKalon Marine & Protective Coatings has no control over either the quality or condition of the substrate, or the many factors affecting the use and application of the product. SigmaKalon Marine & Protective Coatings does therefore not accept any liability arising from loss, injury or damage resulting from such use or the contents of this data sheet (unless there are written agreements stating otherwise).

The data contained herein are liable to modification as a result of practical experience and continuous product development. This data sheet replaces and annuls all previous issues and it is therefore the user's responsibility to ensure that this sheet is current prior to using the product.

The English text of this document shall prevail over any translation thereof.

PDS	7955
202661 grey	5177052200
202662 grey	5163052200
202659 redbrown	6179052200